

## Claims

1. A method for production of sandwich panel core from composites  
5 including the placing of the blank from reinforcing material, the impregnation of  
the blank with binder obtaining thus the prepreg, the hardening of the binder in  
the course of hot-pressing and obtaining of the plane semifinished-blank in the  
form of a set of relatively rigid parts having the form of the core ridges and  
detached of one another for some distance, the after-deformation of the  
10 semifinished-blank and obtaining the core relief with the required geometrics, and  
the final hardening of the applied binder is characterized by that the reinforcing  
material is impregnated with binder along the full surface of the blank, the heat  
supply for hardening of the binder in the obtained prepreg within the bounds of  
said parts, and creation of conditions slowing down the process of hardening  
15 along the prepreg zones between said parts.

2. A method according to claim **1** is characterized by that width of the  
prepreg zones between the parts having the form of the core ridges is provided in  
the course of hot-pressing and is not less than double radius of the blank material  
bending at these parts when shaping the core.